



FEEL THE SW DIFFERENCE®

DESIGNED TO ENHANCE WORKER PERFORMANCE.



PF-95LG

POWDER-FREE ECOTEK SUSTAINABLE NITRILE SINGLE-USE GLOVES WITH ENERGEL®

ECOTEK BIODEGRADABLE GLOVE THAT COMBINES TACTILE SENSITIVITY WITH ENERGEL TECHNOLOGY TO SOOTHE AND HYDRATE SKIN*

- EnerGel® Hand Conditioning Technology hydrates and soothes skin
- EcoTek® Sustainability Technology accelerates landfill break-down without any performance loss
- Tested for use with chemotherapy drugs
- Optimal thickness for durability and tactile sensitivity
- Fully textured surface for excellent wet and dry grip
- Silicone-free to prevent contamination
- Tear-resistant beaded cuff eases donning
- SHA Dermatologically Approved
- 1.5 AQL exceeds laboratory standards



Optimal thickness for durability and tactile sensitivity

Fully textured surface for wet and dry grip

Tear-resistant beaded cuff for easy donning

PF **PF-95LG**

WEIGHT	LENGTH	THICKNESS	FEATURES	COLOR
7.0g (large size)	9.5"	5.1 mil	EnerGel® EcoTek®	LIGHT GREEN

ECOTEK



SW®
33278 Central Avenue, Unit 102, Union City, CA 94587, USA
Tel: +1.510.429.8692 | Fax: +1.510.487.5347

Trademarks and registered trademarks are the property of SW and its affiliates.
©2023 SW. All rights reserved.



TECHNICAL DATA



PF-95LG

POWDER-FREE ECOTEK SUSTAINABLE
NITRILE SINGLE-USE GLOVES WITH ENERGEL*

PRODUCT DESCRIPTION

SPECIFICATIONS

PRODUCT	PowerForm®		
GRADE	Powder-Free Exam		
MATERIAL	Nitrile		
THICKNESS	FINGER	5.9mil	0.15mm
	PALM	5.1mil	0.13mm
	CUFF	4.0mil	0.10mm
COLOR	Light Green		
SURFACE	OUTER	Fully Textured	
	INNER	EnerGel®	
LENGTH	9.5"	242mm	
WEIGHT	7.0 g		
FIT TYPE	Ambidextrous		
CUFF TYPE	Beaded		
WATERTIGHT AQL	1.5		
ORIGIN COUNTRY	China		

* Specifications based on size Large glove

PHYSICAL PROPERTIES

	PRE-AGING	POST-AGING
TENSILE STRENGTH:	14 MPa	14 MPa
ELONGATION:	500%	400%

INTEGRATED TECHNOLOGIES

ENERGEL Hand Conditioning Technology: allows for thorough penetration of aloe vera into the skin, reduces water loss to retain moisture and has been clinically proven to prevent many skin ailments, like dermatitis.

ECOTEK Sustainability Technology: 92.6% waste reduction in 2.5 years. ASTM D5526-12 test results do not predict future biodegradation.*



STANDARDS & CERTIFICATIONS

EN ISO 21420:2020
EN 455-2000-2015
ASTM D6319-19
ASTM D6978-05 (2019)
ASTM F1671-13
ASTM F739-12
Reach EU 1907/2006

EU 2016/425
CAT III Complex Design
UL NFPA 1999-2018
FDA 21 CFR 177.2600



Please visit swssglobal.com/symbols for information on standards used on this document.

ORDERING

ITEM NO.	SIZE	PALM WIDTH	PACKAGING
N129401	XS 5½ – 6	3.0" 75mm	100 gloves per box 10 boxes per case
N129402	S 6½ – 7	3.1" 80mm	100 gloves per box 10 boxes per case
N129403	M 7½ – 8	3.4" 87mm	100 gloves per box 10 boxes per case
N129404	L 8½ – 9	4.0" 101mm	100 gloves per box 10 boxes per case
N129405	XL 9½ – 10	4.5" 114mm	100 gloves per box 10 boxes per case
N129406	2XL 10½ – 11	4.8" 123mm	100 gloves per box 10 boxes per case

APPLICATIONS

For Medical Use
Chemical Handling
Clinical
Laboratory
Light Chemical Mixing
Pharma Production

Keep out of sunlight. Store in a cool, dry place.
Keep away from sources of ozone or ignition.



R_N12940X0323



SW®
33278 Central Avenue, Unit 102, Union City, CA 94587, USA
Tel: +1.510.429.8692 | Fax: +1.510.487.5347
Trademarks and registered trademarks are the property of SW and its affiliates.
©2023 SW. All rights reserved.



*Under test method ASTM D5526-12, a standard test method for determining anaerobic biodegradation of plastics in accelerated landfill conditions. Current biodegradation results do not predict future results.