



FEEL THE SW DIFFERENCE®

COMFORT AND DEXTERITY FOR EVERYDAY HAND PROTECTION.




TF-95LG

POWDER-FREE NITRILE EXAMINATION GLOVES WITH ECOTEK SUSTAINABLE TECHNOLOGY, ENERGEL & PH NATURAL

VALUE AND PERFORMANCE HAND PROTECTION FOR MEDICAL ENVIRONMENTS

- EcoTek® Sustainable Technology*
- Proprietary pH Natural® coating supports the skin's natural pH to help discourage microbial growth that can lead to infection
- EnerGel® Hand Conditioning Technology clinically proven to hydrate and soothe skin
- Exceeds 1.5 AQL laboratory standards
- Touch-screen compatible
- Tear-resistant beaded cuff eases donning
- SHA Dermatologically Approved



Finger textured surface for wet and dry grip

Optimal thickness for durability and tactile sensitivity

Tear-resistant beaded cuff for easy donning

TF **TF-95LG**

WEIGHT	LENGTH	THICKNESS	FEATURES	COLOR
4.8g (large size)	9.5"	4.0 mil 3.6 mil	EcoTek® pH Natural® EnerGel®	LIGHT GREEN

ECOTEK



SW®
33278 Central Avenue, Unit 102, Union City, CA 94587, USA
Tel: +1.510.429.8692 | Fax: +1.510.487.5347
Trademarks and registered trademarks are the property of SW and its affiliates.
©2025 SW. All rights reserved.



TECHNICAL DATA



TF-95LG

POWDER-FREE NITRILE EXAMINATION GLOVES WITH ECOTEK SUSTAINABLE TECHNOLOGY, ENERCEL & PH NATURAL

POLYCARBIN

THIS GLOVE IS RECYCLABLE THROUGH POLYCARBIN'S LAB RECYCLING PROGRAM.



PRODUCT DESCRIPTION

SPECIFICATIONS

PRODUCT	TrueForm®
GRADE	Powder-Free Exam
MATERIAL	Nitrile
THICKNESS	FINGER 4.0mil 0.10mm
	PALM 3.6mil 0.09mm
	CUFF 3.0mil 0.08mm
COLOR	Light Green
SURFACE	OUTER Finger Textured
	INNER EnerGel®
LENGTH	9.5" 242mm
WEIGHT	5.0g
FIT TYPE	Ambidextrous
CUFF TYPE	Beaded
WATERTIGHT AQL	1.5
ORIGIN COUNTRY	Malaysia

PHYSICAL PROPERTIES

	PRE-AGING	POST-AGING
TENSILE STRENGTH:	22MPA	20 MPA
ELONGATION:	560%	550%

INTEGRATED TECHNOLOGIES

pH NATURAL Hand Health Technology: Controls pH levels of the skin to discourage microbial growth that can lead to infection

ENERGEL Hand Conditioning Technology: allows for thorough penetration of Aloe Vera into the skin, reduces water loss to retain moisture and has been clinically proven to prevent many skin ailments, like dermatitis.

ECOTEK Sustainable Technology: Product has been tested per ASTM D5526*

* Specifications based on size Large glove

STANDARDS & CERTIFICATIONS

EN ISO 21420:2020
EN 455-2000-2015
ASTM D6319-19
ASTM F1671-13
ASTM F739-12
Reach EU 1907/2006
EU 2016/425

CAT III Complex Design
FDA 21 CFR 177.2600



Please visit swssglobal.com/symbols for information on standards used on this document.

ORDERING

ITEM NO.	SIZE	PALM WIDTH	PACKAGING
N028401	XS 5½ – 6	3.0" 75mm	100 gloves per box 10 boxes per case
N028402	S 6½ – 7	3.3" 85mm	100 gloves per box 10 boxes per case
N028403	M 7½ – 8	3.7" 95mm	100 gloves per box 10 boxes per case
N028404	L 8½ – 9	4.1" 105mm	100 gloves per box 10 boxes per case
N028405	XL 9½ – 10	4.5" 115mm	100 gloves per box 10 boxes per case

APPLICATIONS

- For Medical Use
- Chemical Handling
- Clinical
- First Responder EMS
- Handling and Packaging Class 1
- Medical Devices
- Laboratory
- Light Chemical Mixing
- Pharma Production

Keep out of sunlight. Store in a cool, dry place. Keep away from sources of ozone or ignition.



R_N02840X0825



SW®
33278 Central Avenue, Unit 102, Union City, CA 94587, USA
Tel: +1.510.429.8692 | Fax: +1.510.487.5347

Trademarks and registered trademarks are the property of SW and its affiliates.
©2025 SW. All rights reserved.



*EcoTek gloves tested to ASTM D5526-12 Standard Test Method for Determining Anaerobic Biodegradation of Plastic Materials Under Accelerated Landfill Conditions. Results are 92.6% biodegradation in 60% solids landfill at 945 days. Future results cannot be predicted/extrapolated. If you need more information on the test reports, send email to cs@swssglobal.com.